

Roofing bituminous sealant Döcke

1. Description.

Roofing bituminous sealant Döcke – bitumen-based, contains processing aids and solvent.

2. Purpose of the product.

Sealing of joints, junctions on concrete, wooden, metal and plastic surfaces; encapsulation of rain gutter systems with adhesive connection; roofing repair works; installation of various roofing materials, crack repair.

3. Features of works with the product.

- The processed surface must be dry, preliminary cleaned out from dirt and undurable leftovers of previous cover. Applied with a construction pistol. The thickness of layer of the pressed out sealant is regulated by the proper cut on the cartridge nose.
- In case of works at low temperatures it is recommended to warm up the sealant for 24 hours at the temperature not lower than +15 °C. It is allowed to work with the sealant at the temperature not lower than -10 °C.
- Consumption of the sealant depends on the type of works performed.



4. Physical and mechanical characteristics

| № | Indicator | Normative value, units amesure |
|---|--|--------------------------------|
| 1 | Mass fraction of non-volatile inclusions | 70-80 % |
| 2 | The softening point of the dry residue | not less than 110 °C |
| 3 | Adhesion strength with metal | not less than 0,1 MPa |
| 4 | Adhesion strength with concrete | not less than 0,1 MPa |
| 5 | Water absorption within 24 hours | not more than 0,4 % by weight |
| 6 | Flexibility on the beam, r=5 mm, at -15 °C | no cracks |

5. Logistical characteristics

| № | Indicator, unit of measurement | Normative value |
|---|--------------------------------|-----------------|
| 1 | Net weight of 1 piece, kg | 0,28 |
| 2 | Weight of 1 piece gross, kg | 0,3 |
| 3 | Volume 1 piece, l | 0,31 |
| 4 | Quantity in a package, pcs | 12 |
| 5 | Gross weight of 1 package, kg | 3,67 |
| 6 | Packing dimensions (LxWxH), mm | 215x160x255 |
| 7 | Quantity on a pallet, pcs | 1440 |
| 8 | Pallet gross weight, kg | 466 |

6. Rules of storage.

Store in original packaging at temperatures from -30 to +50 °C. Protect from moisture and direct sunlight, away from heaters and open sources of fire. Do not store indoors or in contact with foodstuffs. Keep out of the reach of children. Guaranteed shelf life in sealed packaging - 24 months.

Technical support service: 8 800 100 71 45, www.docke.ru.